

Product Information

ROHACELL® RIMA

RIGID FOAM WITH A FINE CELL STRUCTURE

ROHACELL® RIMA is a closed-cell rigid foam based on polymethacrylimide (PMI) chemistry that is completely free of CFC's and specially designed to ensure the minimum possible uptake of resin.

USE LESS RESIN. SAVE WEIGHT AND COSTS.

The fine, closed-cell structure of ROHACELL® RIMA provides the unique benefit of allowing a minimal resin uptake of only approx. 50 g/m².

This eliminates excess and unnecessary resin that adds undesirable weight and cost to a finished part.

The end weight of the finished component remains extremely low.

PROCESSING AND PRODUCTION

ROHACELL® RIMA foam is particularly well-suited for vacuum infusion and RTM processes where the fine-cell foam can also be used purely as a fly-away tool.

Processing is possible at a pressure of 0.7 MPa (102 psi) and temperatures up to 130 °C (266 °F).

Heat-treated ROHACELL® RIMA-HT can be used at a temperature of 180 °C (356 °F) and pressures up to 0.7 MPa (102 psi).

THERMOFORMING AND SHAPING

ROHACELL® RIMA can be easily thermoformed or CNC machined to meet customer requirements.

High precision, pre-shaped and ready-to-use foam cores in complex or simple geometries can also be supplied by the ROHACELL® Shapes Department.

Property	Test Method*	Unit	ROHACELL® 51 RIMA	ROHACELL® 71 RIMA	ROHACELL® 110 RIMA
Density	ISO 845 ASTM D 1622	kg/m ³ lbs/ft ³	52 3.25	75 4.68	110 6.87
Compressive Strength	ISO 844 ASTM D 1621	MPa psi	0.8 116	1.7 246	3.6 522
Tensile Strength	ISO 527-2 ASTM D 638	MPa psi	1.6 232	2.2 319	3.7 536
Tensile Modulus	ISO 527-2 ASTM D 638	MPa psi	75 10,875	105 15,225	180 26,100
Elongation at Break	ISO 527-2 ASTM D 638	%	7	7	7
Shear Strength	DIN 53294 ASTM C 273	MPa psi	0.8 116	1.3 188	2.4 348
Shear Modulus	DIN 53294 ASTM C 273	MPa psi	24 3,480	42 6,090	70 10,170
Coefficient of Thermal Expansion		1/K*10E-5	4.06	3.40	3.64

Technical data values presented above are typical for nominal density, subject to normal manufacturing variations. *Data values are based on ISO & DIN standard test methods, however ASTM values can be confirmed upon request. All ROHACELL® products are closed-cell rigid foams based on polymethacrylimide (PMI) chemistry and contain no CFC's.

FOR MORE INFORMATION

If you have questions or would like to discuss using **ROHACELL® RIMA** in your application, we encourage you to talk with your local ROHACELL® representative.

Visit www.rohacell.com to locate and directly connect with the contact in your region, by phone or email.

Disclaimer

ROHACELL® is a registered trademark of Evonik Industries and its subsidiaries.

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

Evonik Operations GmbH | Smart Materials

High Performance Polymers
Performance Foams
64293 Darmstadt, Germany
Phone +49 61 51 18-1005

Evonik Corporation

Theodore, Alabama USA
Phone +1 866 764-6235

**Evonik Specialty Chemicals
(Shanghai) Co., Ltd.**

Shanghai, China
Phone +86 21 6119 1544